
DURA+SKRIM® 6BB, 6WB & 6WW

Four-Layer Reinforced Extrusion Laminate



Product Description

DURA+SKRIM® 6BB, 6WB & 6WW are economical, reinforced films designed for applications requiring puncture resistance and high tear strengths. A heavyduty scrim reinforcement, laminated between two layers of virgin highstrength polyethylene film, results in a material that resists punctures and immediately stops



tears. The addition of carbon black and ultra violet inhibitors to DURA+SKRIM® 6BB, 6WB and 6WW, respectively, increases outdoor longevity. DURA+SKRIM® 6 is the first choice for applications requiring greater performance than common 6 and 10 mil plastic sheeting.

Product Use

DURA+SKRIM® 6BB, 6WB & 6WW are used in short to mid-term applications requiring a light weight, tear-resistant, reinforced film. The white side of DURA+SKRIM® 6WB and 6WW are excellent choices for covering applications that require minimal heat build up and condensation. DURA+SKRIM® 6WW meets or exceeds ASTM E-1745, Class "C" standard as an underslab vapor retarder and is an excellent choice as an in-wall and roof vapor retarder as well.

Size & Packaging

DURA+SKRIM® 6BB, 6WB & 6WW are available in a variety of widths and lengths. Panel sizes up to 100,000 square feet are available. All panels are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time-saving installation.





Construction Site Covers

| Product | Part # |
|----------------|--------|
| DURA•SKRIM 6BB | R6BB |
| DURA•SKRIM 6WB | R6WBK |
| DURA+SKRIM 6WW | R6WWK |

APPLICATIONS

| Construction Site Covers | Insulation Membrane |
|--------------------------|---------------------|
| | |

Temporary Erosion Control

Concrete Curing Covers Lumber Covers

Shipping Covers

Pallet Covers

Remediation Covers

Cargo Wraps

es

Building Enclosures

Silage Covers

Temporary Walls

Fumigation Covers

DURA+SKRIM® 6BB, 6WB & 6WW

ISO 9001:2008 CERTIFIED MANAGEMENT SYSTEM

Four-Layer Reinforced Extrusion Laminate

| | | DURA+SKRIM 6BB | | DURA•SKRIM 6WB | | DURA•SKRIM 6WW | | |
|--------------------------|-------------------------|--|---------------------------------|--------------------------------------|---------------------------------|--------------------------------------|----------------------------------|--|
| PROPERTIES | TEST | Imperial | METRIC | I MPERIAL | METRIC | IMPERIAL | METRIC | |
| Appearance | | Black/Black | | White/Black | | White/White | | |
| THICKNESS, NOMINAL | | 6 mil | 0.15 mm | 6 mil | 0.15 mm | 6 mil | 0.15 mm | |
| WEIGHT | | 24 lbs/MSF 3.5 oz/yd ² | 117 g/m ² | 27 lbs/MSF 3.9 oz/yd ² | 132 g/m ² | 28 lbs/MSF 4.0 oz/yd ² | 137 g/m ² | |
| Construction | | Extrusion laminated with scrim reinforcement | | | | | | |
| 1" Tensile Strength | ASTM D7003 | 60 lbf/in | 105 N/cm | 60 lbf/in | 105 N/cm | 60 lbf/in | 105 N/cm | |
| ELONGATION AT FILM BREAK | ASTM D7003 | 500 % | 500 % | 500 % | 500 % | 500 % | 500 % | |
| GRAB TENSILE | ASTM D7004 | 75 lbf | 333 N | 75 lbf | 333 N | 75 lbf | 333 N | |
| *Trapezoid Tear | ASTM D4533 | 45 lbf | 200 N | 45 lbf | 200 N | 45 lbf | 200 N | |
| MULLEN BURST | ASTM D751 | 50 psi | 345 kPa | 50 psi | 345 kPa | 50 psi | 345 kPa | |
| MAXIMUM USE TEMPERATURE | | 180°F | 82°C | 180°F | 82°C | 180°F | 82°C | |
| MINIMUM USE TEMPERATURE | | -70°F | -57°C | -70°F | -57°C | -70°F | -57°C | |
| WVTR | ASTM E96 Procedure B | 0.292 grains/(100in²-day) | 0.293 g/(m²·day) | 0.292 grains/(100in²-day) | 0.293 g/(m²·day) | 0.292 grains/(100in²-day) | 0.293 g/(m ² ·day) | |
| PERM RATING | ASTM E96 Procedure B | 0.04 Perms grains/(ft²-hr·in Hg) | 0.03 Perms g/(24hr·m²·mm Hg) | 0.04 Perms grains/(ft²-hr-in Hg) | 0.03 Perms g/(24hr·m²·mm Hg) | 0.04 Perms grains/(ft²-hr·in Hg) | 0.03 Perms g/(24hr·m²·mm Hg) | |

^{*}Tests are an average of diagonal directions.



DURA SKRIM® 6BB, 6WB & 6WW are four-layer reinforced extrusion laminates. The outer layers consist of a high-strength polyethylene. Carbon black in the 6BB and UV stabilizers in the 6WW increase longevity.

DURA SKRIM® 6BB, 6WB & 6WW are reinforced with a minimum of 1000 denier scrim laid in a diagonal pattern spaced 3/8" apart.

DURA SKRIM® 6WW meets or exceeds ASTM E-84 standard, Class "A" for surface burning characteristics of building materials and also ASTM E-1745, Class "C" standard for water vapor retarders used in contact with soil or granular fill under concrete slabs.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. RAVEN INDUSTRIES MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.RavenEFD.com



5 Scan C