



Technical Data Sheet

NCFI Polyurethanes

Div. of Barnhardt Manufacturing Co.

PO Box 1528 • Mount Airy, NC 27030

800-346-8229

www.NCFI.com

EnduraTech® Q (70-014)

ACRYLIC ELASTOMERIC COATING

DESCRIPTION:

EnduraTech® Q (70-014) is a durable 100% acrylic elastomeric coating designed specifically for use over new spray polyurethane foam (SPF) roofing systems, or for recoating existing SPF roofing systems.

DISTINGUISHING CHARACTERISTICS:

- Superior resistance to ultraviolet degradation
- Excellent adhesion to SPF
- Good low temperature flexibility down to -15°F
- Low toxicity and odor
- Retains high reflectivity because of excellent dirt pickup resistance, reduces substrate temperatures, prolongs roof life, and reduces interior temperatures and energy costs
- Meets the requirements of ASTM D6083
- Energy Star® Certified Product
- Cool Roof Rating Council (CRRC) Listed

TYPICAL PHYSICAL PROPERTIES:

Properties	Typical Values
Solids by Volume	55%
Solids by Weight	63%
Weight per Gallon	11 lbs.
Viscosity	6500-8500 cps
Coverage, Dry	9 mils/100 ft ² /gal.
Coverage, Wet	16 mils/100 ft ² /gal.
Clean-up	Water
Re-coat Time	2-8 hours

INSTALLATION:

- May be applied by spray or heavy nap roller. However, airless spray is recommended for consistency.
- All surfaces must be clean, dry, and free of dirt, grease, oil, and other contaminants that would interfere with proper adhesion.
- Apply in two separate coats at the minimum rate of one gallon per 100 square feet.
- Apply at temperatures above 50°F.
- Apply only when Weather conditions will permit coating to dry before rain, dew, or freezing temperatures occur.
- For details, see EnduraTech® Application Specifications.

EnduraTech® Q (70-014)

ACRYLIC ELASTOMERIC COATING

PERFORMANCE PROPERTIES:

Properties	Test Method	Typical Values
Elongation	ASTM D2370	200%
Tensile Strength	ASTM D2370	350 psi
Low Temperature Flexibility	ASTM D522	Passes ½" mandrel bend
Permeance @ 20 mils	ASTM D1653	7
Tear Resistance	ASTM D624	63 pli
Adhesion	ASTM D794/D603	3.4 pli
Hardness, Shore A	ASTM D2240	55-65
Accelerated Weathering, 1000 hours	ASTM D4798	No cracking, fading, or checking
Water Swelling	ASTM D471	5%
Solar Reflectance	ASTM C1549	86% initial, 81% aged (white) 66% initial, 65% aged (tan)
Thermal Emittance	ASTM C1371	0.88 initial, 0.91 aged (white) 0.88 initial, 0.89 aged (tan)
SRI (Solar Reflectance Index)	ASTM E1980	108 initial, 102 aged (white) 80 initial, 79 aged (tan)

RATINGS AND APPROVALS:

Organization	Test Method	Rating or Evaluation
Underwriters Laboratories	UL 790	Class A (NC) Class B (C-15/32)
Underwriters Laboratories	UL 1256	Class 90
Underwriters Laboratories	UL 580 Wind Uplift Resistance	165 psf
Underwriters Laboratories	UL 2218	Class 1
ICC Evaluation Services	Evaluation Report	ESR-3392
Cool Roof Rating Council (CRRC)	Approval	0990-001 (white)
		0990-002 (tan)

The information on our data sheets is to assist customers in determining whether our products are suitable for their applications. The customers must satisfy themselves as to the suitability for specific cases. NCFI Polyurethanes warrants only that the material shall meet its specifications; this warranty is in lieu of all other written or unwritten, expressed or implied warranties and NCFI Polyurethanes expressly disclaims any warranty of merchantability, fitness for a particular purpose, or freedom from patent infringement. Accordingly, buyer assumes all risks whatsoever as to the use of the material. Buyer's exclusive remedy as to any breach of warranty, negligence or other claim shall be limited to the purchase price of the material. Failure to adhere strictly to any recommended procedures shall relieve NCFI Polyurethanes of all liability with respect to the material or the use thereof.